

Magnetic Phases of Rare Earth Hexagonal Manganites

S. H. Curnoe^{a,*}, I. Munawar^a

^a*Department of Physics and Physical Oceanography, Memorial University of Newfoundland, St. John's NL, A1B 3X7, Canada*

Abstract

We describe the magnetic phases of hexagonal rare earth manganites RMnO_3 using Landau theory. A minimal model based on four one-dimensional magnetic order parameters is developed.

Key words: RMnO_3 , hexagonal manganites, multi-ferroics, magneto-electric
PACS: 75.10.-b; 75.30.Kz; 75.80.+q

Hexagonal rare earth and yttrium manganites RMnO_3 ($R = \text{Ho, Er, Tm, Yb, Lu, Y or Sc}$) belong to an unusual class of materials known as “multi-ferroics”, which display simultaneously electric and magnetic ordering. Most of the hexagonal manganites are ferroelectric below a very high temperature ($T_{FE} \approx 900$ K) and order magnetically at a lower temperature ($T_N \approx 100$ K). A complex phase diagram involving several different magnetic order parameters has been investigated using second harmonic generation [1,2] and magnetic and heat capacity measurements [3]. The partially filled 4f shell of the Ho, Er, Tm and Yb compounds has been implicated in low temperature region of the phase diagram [4].

Symmetry plays an important role in the analysis of these systems. Group theoretical methods may be used to: *i*) classify spin structures that contribute to magnetic ordering; *ii*) determine coupling between magnetic order parameters and applied fields, including magneto-electric coupling; and *iii*) find phase diagrams derived from Landau free energy expansions. In this article we discuss preliminary results based on analysis of the Landau free energy.

Below T_{FE} , the space group of hexagonal RMnO_3 is #185, $\text{P6}_3\text{cm}$. The corresponding point group C_{6v} has four one-dimensional representations $A_{1,2}$, $B_{1,2}$, and

two two-dimensional representations $E_{1,2}$. These labels are also be used to denote the representations of the magnetic point group which correspond to magnetic order parameters. Multiple copies of every order parameter are possible for the spins of both Mn and rare earth ions. There is an antiferromagnetic spin configuration involving Mn spins in the xy -plane for each 1D order parameter (see Ref. [2]). Additional spin configurations aligned with z for both Mn and R spins yield other 1D order parameters, as listed below. In these cases, the A_2 order parameter is associated with ferromagnetic ordering. Spin configurations for the 2D order parameters $E_{1,2}$ are also allowed, but so far there is no evidence that they appear in the phase diagram. The presence of 1D order parameters yields the corre-

Table 1
 1D order parameters for spin configurations aligned with z .

R (2a)	A_2	$S_{1z} + S_{2z}$
	B_1	$S_{1z} - S_{2z}$
R (4b)	A_1	$S_{1z} + S_{2z} - S_{3z} - S_{4z}$
	A_2	$S_{1z} + S_{2z} + S_{3z} + S_{4z}$
	B_1	$S_{1z} - S_{2z} + S_{3z} - S_{4z}$
	B_2	$S_{1z} - S_{2z} - S_{3z} + S_{4z}$
Mn (6c)	A_2	$S_{1z} + S_{2z} + S_{3z} + S_{4z} + S_{5z} + S_{6z}$
	B_1	$S_{1z} + S_{2z} + S_{3z} - S_{4z} - S_{5z} - S_{6z}$

sponding magnetic space groups $\text{P6}_3\text{cm}$ (A_1), $\text{P6}_3\text{cm}$ (A_2), $\text{P6}_3\text{cm}$ (B_1), and $\text{P6}_3\text{cm}$ (B_2).

* Corresponding author. Tel: 1-709-737-8888 fax: 1-709-737-8739

Email address: curnoe@physics.mun.ca (S. H. Curnoe).

We begin by discussing the generic features of the magnetic phase diagrams of [Ho,Er,Tm,Yb]MnO₃, as shown in Refs. [2,3]. In all compounds, for $H_z = 0$, the first magnetic phase to appear as a function of decreasing temperature is B₂. The A₂ phase appears at lower temperatures and non-zero applied fields, separated from the B₂ phase by a broad region of hysteresis. The A₂ phase appears at zero field only in ErMnO₃. Additional phases A₁ and B₁ appear at low temperatures and fields in HoMnO₃ only. In this case, an intermediate phase between B₂ and B₁ has been found [3].

The order parameters for the phases A_{1,2} and B_{1,2} are denoted by $\eta_{1,2,3,4}$ respectively. The minimal model which describes the A₂-B₂ phases is

$$F = \alpha_2 \eta_2^2 + \beta_2 \eta_4^4 + \alpha_4 \eta_4^2 + \beta_4 \eta_4^4 + \gamma_{24} \eta_2^2 \eta_4^2 - H_z (\rho_1 \eta_2 + \rho_2 \eta_2^3 + \rho_3 \eta_2 \eta_4^2)$$

where α_i , β_i and γ_{ij} and ρ_i are phenomenological coupling constants and H_z is the magnetic field along the c -axis. α_i are temperature dependent and $\beta_i > 0$ is required for stability. In all four compounds α_4 changes sign at $T_N \approx 80$ K. Note that η_2 transforms in the same way as M_z .

This simple model can account for all of the features so far observed. In zero applied field, the model allows for four different phases: (0,0) (the parent phase), which may be connected to either $(\eta_2, 0)$ (A₂-phase), $(0, \eta_4)$ (B₂-phase) or (η_2, η_4) (a mixed phase) by second order phase transitions. These are found by solving the set of coupled equations $\partial F / \partial \eta_i = 0$, subject to the minimisation conditions $(\partial^2 F / \partial \eta_2^2) > 0$ and $(\partial^2 F / \partial \eta_2^2)(\partial^2 F / \partial \eta_4^2) - (\partial^2 F / \partial \eta_2 \partial \eta_4)^2 > 0$. The mixed phase can be a minimum of F only when $4\beta_2\beta_4 > \gamma_{24}^2$. Its existence is *not* the result of hysteresis. The model also allows for the coexistence of two or more different phases by hysteresis. Experiments suggest that in fact there is a first order transition between the B₂-phase and the A₂-phase in all materials with a broad area of hysteresis between, therefore we conclude that $\gamma_{24}^2 > 4\beta_2\beta_4$. Then stability requires that $\gamma_{24} > 0$. Anomalies in the c -axis magnetisation at the B₂ phase boundary [3] are evidence that B₂ and A₂ are coupled. In general η_2 grows linearly with applied field but it will still be subject to a transition in the sense that a change in sign of α_2 will increase the number of minima of the Landau functional.

The low temperature part of the phase diagram of HoMnO₃ contains several additional phases. Neutron diffraction studies [4] indicate that the new phases B₁ and A₁ which appear below 35K are due ordering of the Ho spins, presumably associated with the rather large magnetic moment of the Ho ion. Additional order parameters η_1 and η_3 are required to describe the phases in HoMnO₃. New terms in the free energy take precisely the same form as those involving η_2 and η_4 , as well as a term of the form $\eta_1 \eta_2 \eta_3 \eta_4$. Field dependent terms are

found by replacing η_4 with η_1 and η_3 in the field dependent terms of F , and a term of the form $H_z \eta_1 \eta_3 \eta_4$ is also allowed. This model may be solved exactly in zero applied field, and it is found that the allowed phases are (0,0,0,0) (the parent phase), $(\eta_1, 0, 0, 0)$ *etc.* (A_i or B_i) and $(\eta_1, \eta_2, 0, 0)$ *etc.* (mixed phases involving two order parameters). In addition, hysteresis effects will increase the complexity of the observed phase diagram.

Experimentally, a new intermediate phase between B₂ and B₁ is found at low temperatures [3]. This phase may be a true minimum of F of the form $(0, 0, \eta_3, \eta_4)$ with symmetry P6₃. However, the most recent results show hysteresis *within* the intermediate phase region, which suggests that this phase may actually be further subdivided [5].

Finally, we comment on the magneto-electric effect in HoMnO₃. Linear coupling of magnetic and electric field of the form $\alpha_{ij} E_i H_j$ can only occur in a subset of magnetic point groups in which both inversion symmetry and time reversal symmetry are broken. As noted in [7], magneto-electric coefficients α_{zz} and $\alpha_{xx} = \alpha_{yy}$ may be non-zero in P6₃cm (A₂ order), while $\alpha_{xy} = -\alpha_{yx}$ in P6₃cm (A₁ order). Other coefficients may exist in the presence of E₁ or E₂ magnetic order parameters, if they occur. Magneto-elastic coupling has been observed [6], but this is secondary to the magneto-electric effect, since strain alone cannot induce linear coupling between magnetic and electric orders. In HoMnO₃, evidence of magneto-electric coupling from dielectric anomalies was found in the intermediate B₁-B₂ region [8]. A mixture of B₁ and B₂ order parameters, which would yield P6₃, does not lower the symmetry enough for magneto-electric coupling. Symmetry lowering in the vicinity of domain walls has been proposed [9]. Another possibility is that the magneto-electric effect is due to A₁ domains, since the A₁ phase region is adjoined to regions of hysteresis within the intermediate phase [5].

We thank I. Sergienko for many helpful discussions. This work was supported by NSERC of Canada.

References

- [1] D. Fröhlich, et al. J. Appl. Phys. **85** (1999) 4762.
- [2] M. Fiebig, et al. J. Appl. Phys. **93** (2003) 8194.
- [3] B. Lorenz, et al. Phys. Rev. B **71** (2005) 014438.
- [4] Th. Lonkai, et al. Appl. Phys. A **74** (2002) S843.
- [5] F. Yen, et al. Phys. Rev. B **71** (2005) 180407(R); O. P. Vajik, et al. Phys. Rev. Lett. **94** (2005) 087601.
- [6] C. dela Cruz, et al. Phys. Rev. B **71** (2005) 060407(R).
- [7] T. Lottermoser, et al. Nature **430** (2004) 541.
- [8] B. Lorenz, et al. Phys. Rev. Lett. **92** (2004) 087204.

- [9] T. Lottermoser and M. Fiebig, Phys. Rev. B **70** (2004) 220407(R).